



Temperatura: Max.200°C

Material: Poliuretano

Presión max. de trabajo: 350 bar

Artículo	Ø ext	Ø in	Tamaño
JBR08	25.40	17.02	1/2"
JBR12	31.72	23.36	3/4"
JBR16	39.62	31.24	1"
JBR20	44.45	36.07	1"1/4
JBR24	53.98	45.34	1"1/2
JBR32	63.50	54.86	2"

PROPERTIES	METHOD	MEASURE UNIT	SPECIFICATIONS	FOUND DATA
Melt flow index	ISO 1133	g/10' 220°C 3,80 Kg	15 -40	20
Hardeness Shore A	DIN 53505		92,0 -96,0	95.9
Tensile strength	DIN 53504	Mpa	>=30	35
Modulus 100%	DIN 53504	Mpa	>=7	11
Modulus 300%	DIN 53504	Mpa	>=15	23
Elongation at brake	DIN 53504	%	>=425	502